

### Typical Performance of Pyropel Products to Chemical Attack

Chemicals	Concentration	Temperature	Time	% Strength
	%	OC	Hrs.	Retention
Sulfuric Acid	5	95	100	55-65
	10	20	100	85-95
	20	50	100	75-85
	70	20	100	60-70
Nitric Acid	10	20	100	85-95
	30	20	100	75-85
	30	50	24	75-85
Hydrochloric Acid	10	95	10	40-50
	20	50	24	65-75
	37	20	10	75-85
	37	20	100	45-55
Acetic Acid	100	20	1000	85-95
Formic Acid	85	20	1000	75-85
Benzoic Acid	Saturated	95	10	85-95
Benzoic Acid	Saturated	20	1000	85-95
Oxalic Acid	Saturated	20	1000	90-100
Sodiumhydroxide	5	20	100	0
Ammoniumhydroxide	5	20	100	0
			1000	
Acetone	100	20	168	85-95
Perchloroethylene	100	70	1000	90-100
Benzene	100	20	1000	90-100
Gasoline	100	20	1000	90-100
Ethylene Glycol	100	20	1000	85-95
Sodiumhypochlorite	0.4	20	10	90-100
Sodiumchlorite	0.5	20	10	90-100
Sodiumchlorite	0.5	50	10	90-100
Sodiumchlorate	0.5	50	100	90-100
Hydrogenperoxide	0.5	50	100	90-100

All statements and technical information contained herein are based on tests we believe to be reliable. There is no guarantee of the accuracy and completeness of the information and the following is made in lieu of all warranties, expressed or implied. User shall determine the suitability of the product for his intended use and assumes all risk and liability whatsoever in connection therewith.