

High-Purity Thermoset Polyimide
Data Sheet

PROPERTY	Temp OF	ASTM	UNITS	VALUE
Mechanical	73	D-638	psi	10000
Tensile Strength	500			5970
Elongation	73	D-638	%	2
	500			3.8
Flexural Strength	73	D790	psi	13000
	500			7890
Flexural Modulus	73	D790	psi	550000
	500			303000
Compressive Stress	73	D-695	psi	
1% Strain				3900
10% Strain				31000
Compressive Modulus	73	D-695	psi	540000
Impact Strength, Notched Izod	73	D-256	ft-lb/in	0.8
Thermal	212	D696	10-6in/in/OF	23
Coefficient of Linear Expansion				
Continuous Use Temperature				5500F
Thermal Conductivity	400	C-177		2.09
Deformation under load @2000 psi	500	D-621	%	0.59
Deflection temperature @ 264 psi		D-648	0 F	610
Electrical	73	D-150		3.59
Dielectric Constant @ 50 Hz				
Dielectric Strength	73	D-150	Volts/mil	412
Volume Resistivity	73	D-257	ohm-cm	1.0x10 ¹⁸
Surface Resistivity	73	D-257	ohms	1x10 ¹⁷
Other Properties	122	D-570	% @ 24 hrs.	0.2
Water Absorption			% @ 48 hrs.	0.58
Specific Gravity		D-792		1.35
Flammability Rating		UL94		94V-0

All statements and technical information contained herein are based on tests we believe to be reliable. There is no guarantee of the accuracy and completeness of the information and the following is made in lieu of all warranties, expressed or implied. User shall determine the suitability of the product for his intended use and assumes all risk and liability whatsoever in connection therewith.